


GARR TOOL Milling Guide for X5/G5

ISO Material		HRC	SFM (Vc)								
				3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"
S	COBALT BASE ALLOYS										
	Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 40 > 40	120 - 240 100 - 195	.0005" - .0015" .0004" - .0012"	.0008" - .0020" .0006" - .0018"	.0009" - .0022" .0008" - .0020"	.0011" - .0024" .0009" - .0022"	.0016" - .0034" .0012" - .0029"	.0018" - .0041" .0014" - .0036"	.0022" - .0050" .0018 - .0046	.0032" - .0070" .0024" - .0060"
	NICKEL BASE ALLOYS										
	Invar, Kovar, Inconel-625/718, Waspaloy, Rene, Hastelloy, A286	< 40 > 40	120 - 240 100 - 195	.0005" - .0015" .0004" - .0012"	.0008" - .0020" .0006" - .0018"	.0009" - .0022" .0008" - .0020"	.0011" - .0024" .0009" - .0022"	.0016" - .0034" .0012" - .0029"	.0018" - .0041" .0014" - .0036"	.0022" - .0050" .0018 - .0046	.0032" - .0070" .0024" - .0060"
	IRON BASE ALLOYS										
	Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 40 > 40	120 - 240 100 - 195	.0005" - .0015" .0004" - .0012"	.0008" - .0020" .0006" - .0018"	.0009" - .0022" .0008" - .0020"	.0011" - .0024" .0009" - .0022"	.0016" - .0034" .0012" - .0029"	.0018" - .0041" .0014" - .0036"	.0022" - .0050" .0018 - .0046	.0032" - .0070" .0024" - .0060"
	MONEL										
	Monel - 65% Nickel		160 - 290	.0005" - .0015"	.0008" - .0020"	.0009" - .0022"	.0011" - .0024"	.0016" - .0034"	.0018" - .0041"	.0022" - .0050"	.0032" - .0070"
	TITANIUM ALLOYS										
	Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		260 - 490	.0005" - .0015"	.0009" - .0019"	.0010" - .0020"	.0012" - .0026"	.0018" - .0038"	.0020" - .0046"	.0024" - .0054"	.0036" - .0078"
5553 / Beta Titanium		195 - 365	.0004" - .0012"	.0009" - .0017"	.0010" - .0019"	.0012" - .0024"	.0018" - .0034"	.0020" - .0041"	.0024" - .0050"	.0032" - .0070"	
M	STAINLESS STEELS										
	13/8, 15/5, 17-4, pH Types	< 40 > 40	290 - 490 225 - 360	.0005" - .0015" .0004" - .0011"	.0007" - .0018" .0006" - .0015"	.0008" - .0020" .0007" - .0019"	.0011" - .0024" .0009" - .0022"	.0016" - .0034" .0012" - .0029"	.0018" - .0041" .0014" - .0037"	.0022" - .0050" .0018" - .0046"	.0032" - .0070" .0024" - .0060"
	200 Series, 300 Series	< 40 > 40	355 - 555 290 - 455	.0005" - .0015" .0004" - .0010"	.0007" - .0018" .0006" - .0015"	.0008" - .0020" .0007" - .0019"	.0011" - .0024" .0009" - .0022"	.0016" - .0039" .0012" - .0029"	.0018" - .0046" .0014" - .0037"	.0022" - .0056" .0018" - .0046"	.0032" - .0080" .0024" - .0060"
	304L, 316L, Nitronic 50	< 40 > 40	325 - 520 225 - 360	.0005" - .0015" .0004" - .0009"	.0007" - .0018" .0006" - .0014"	.0008" - .0020" .0007" - .0019"	.0011" - .0024" .0009" - .0022"	.0016" - .0034" .0012" - .0029"	.0018" - .0041" .0014" - .0037"	.0022" - .0050" .0018" - .0046"	.0032" - .0070" .0024" - .0060"
	400 Series	< 40 > 40	290 - 555 225 - 425	.0005" - .0015" .0004" - .0009"	.0007" - .0018" .0006" - .0014"	.0008" - .0020" .0007" - .0019"	.0011" - .0026" .0009" - .0023"	.0016" - .0036" .0012" - .0032"	.0018" - .0044" .0014" - .0039"	.0022" - .0054" .0018" - .0048"	.0032" - .0074" .0024" - .0066"
	P	HIGH STRENGTH TOOL STEELS									
A2, D2, P20, H13, S7, O1		< 40 > 40	290 - 520 195 - 425	.0006" - .0014" .0005" - .0010"	.0008" - .0018" .0007" - .0014"	.0009" - .0022" .0008" - .0018"	.0013" - .0026" .0012" - .0022"	.0016" - .0036" .0012" - .0029"	.0022" - .0044" .0020" - .0036"	.0026" - .0054" .0024" - .0046"	.0040" - .0074" .0036" - .0060"
MEDIUM ALLOY TOOL STEELS											
4140, 4340, 52100, 6150, 8620		< 40 > 40	455 - 650 325 - 490	.0006" - .0014" .0005" - .0010"	.0008" - .0019" .0007" - .0014"	.0009" - .0023" .0008" - .0018"	.0013" - .0027" .0012" - .0022"	.0016" - .0038" .0012" - .0031"	.0022" - .0046" .0020" - .0038"	.0026" - .0056" .0024" - .0046"	.0040" - .0078" .0036" - .0064"
CARBON STEELS											
1000's - 1018, 1020, 12L14	< 40	490 - 780	.0006" - .0014"	.0010" - .0015"	.0009" - .0018"	.0013" - .0028"	.0020" - .0041"	.0022" - .0048"	.0026" - .0058"	.0040" - .0084"	
K	CAST MATERIAL										
	Steel (Malleable)		455 - 685	.0006" - .0019"	.0009" - .0023"	.0010" - .0025"	.0015" - .0029"	.0020" - .0044"	.0026" - .0051"	.0030" - .0060"	.0040" - .0090"
	Ductile Iron		455 - 685	.0006" - .0019"	.0009" - .0023"	.0010" - .0025"	.0015" - .0029"	.0020" - .0044"	.0026" - .0051"	.0030" - .0060"	.0040" - .0090"
	Gray Iron		585 - 770	.0007" - .0019"	.0010" - .0022"	.0011" - .0026"	.0016" - .0030"	.0022" - .0046"	.0026" - .0053"	.0032" - .0062"	.0044" - .0094"

	Profile/Trochoidal Milling
Axial (ap)	up to 2xD
Radial (ae)	5% - 25% of Dia.



NOTE - DATA DOES NOT REFLECT CHIP THINNING.

SPINDLE INTERFACE MUST BE SCRUTINIZED WHEN USING 5/8" DIAMETER AND LARGER END MILLS

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.